

## LD-Quarzglas-Rohre

LD Quarzglas – Rohre werden in Einzelfertigung mittels Glasbläserdrehbank bearbeitet. Außendurchmesser und Wanddicke können frei gewählt werden.

Außendurchmesser(mm)	Außendurchm.-Toleranz(mm)	Wanddickenbereich	
		Min.(mm)	Max.(mm)
50	±0,7	1,5	7
60	±1,0	2	7
70	±1,0	2,5	7
80	±1,0	2,5	8
90	±1,0	2,5	8
100	±1,0	2,5	10
110	±1,0	2,5	10
120	±1,5	3	10
130	±1,5	3	10
140	±1,5	3	10
150	±1,5	3,5	12
160	±1,5	3,5	12
170	±2,0	3,5	12
180	±2,0	4	12
190	±2,0	4	12
200	±2,0	4	12
210	±2,0	4	10
220	±2,0	4	10
225	±2,0	4	10
230	±2,0	4	10
240	±2,0	4	10
250	±2,0	4	10
260	±2,0	4	10
270	±2,0	4	10
280	±2,0	4	10
290	±2,0	4	10
300	±2,0	4	10
310	±2,0	4	8
320	±2,0	4	8
330	±2,0	4	8
340	±2,0	4	8
350	±2,0	4	8
360	±2,0	4	8
370	±2,0	4	8
380	±2,0	4	8
390	±2,0	4	8
400	±2,0	4	8
410	±2,0	4	7
420	±2,0	4	7

430	±2,0	4	7
440	±2,0	4	7
450	±2,0	4	7
460	±2,0	4	7
470	±2,0	4	7
480	±2,0	4	7
490	±2,0	4	7
500	±2,0	4	7
510	±2,5	4	7
520	±2,5	4	7
530	±2,5	4	7
540	±2,5	4	7
550	±2,5	4	7
560	±2,5	4	7
570	±2,5	4	7
580	±2,5	4	7
590	±2,5	4	7
600	±2,5	4	7
610	±2,5	4	7
620	±2,5	4	7
630	±2,5	4	7
640	±2,5	4	7
650	±2,5	4	7
660	±2,5	4	7
670	±2,5	4	7
680	±2,5	4	7
690	±2,5	4	7
700	±2,5	4	7
710	±2,5	4	7
720	±2,5	4	7
730	±2,5	4	7
740	±2,5	4	7
750	±2,5	4	7
760	±2,5	4	7
770	±2,5	4	7
780	±2,5	4	7
790	±2,5	4	7
800	±2,5	4	7
810	±2,5	4	7
820	±2,5	4	7
830	±2,5	4	7
840	±2,5	4	7
850	±2,5	4	7

Aufgrund der Flammenbehandlung beim Aufblasen werden in den oberflächennahen Schichten OH-Gruppen aufgenommen. Somit kann der OH-Gehalt gegenüber der allgemeinen Materialspezifikation abweichen. Weitere Abmessungen auf Anfrage.